



Figure 3. Spectral subtraction result (Sample #1 – Sample #2).

CONCLUSIONS:

Infrared spectroscopic analysis of the foams suggests that the foam with shrinkage problem (sample #2) have lower Polymeric MDI-to-polyol ratio (index) and lower carbodiimide content than the control foam (sample #1).